

ASPHALT CORES										
Sample No.	STATIONS	Thickness (cm)	Wt. In Air (g)	Wt. in Water (g)	Wt. In SSD (g)	VOLUME (cm³)	Gmb (g/cm³)	Gmm (g/cm³)	Compaction (%)	Required Compaction (%)
1	STA 0+010	6.2	946	553	948	395	2.395	2.619	91.4	
2	STA 0+035	6.3	961	558	965	407	2.361	2.619	90.2	
3	STA 0+055	6.3	960	567	966	399	2.406	2.619	91.9	
4	STA 0+095	6.4	966	568	971	403	2.397	2.619	91.5	
5	STA 0+135	7.3	1060	625	1066	441	2.404	2.619	91.8	
6	STA 0+160	7.9	1059	641	1104	463	2.374	2.619	90.6	
7	STA 0+190	7.2	1042	601	1048	447	2.331	2.619	89.0	



Room 372575 commercial Jeddah, license 142, Commercial Registration 4030391463
Email: lab@proficiencylabb.com www.proficiencylabb.com Mob: 0552210350
30 St. - Ar Rabywah Dist. - Jeddah - Kingdom of Saudi Arabia

